

### **Technical Data Sheet**

# Anticor™ C6N Corrosion Inhibitor

Article number: A80447 Verification date: 18/02/2025 Version: 2.1

Typical chemical and physical properties

Excellent aluminium, copper and ferrous corrosion inhibitor. It can be used in acidic as well as alkaline media. It is soluble in mineral oils and esters and dispersible in water.

Proprietary mixture of mono- and di-phosphate esters and surface-active ingredients.

Appearance Yellow/brownish liquid

Phosphorus content ~9%

Solubility

Water Dispersible
Mineral oil Soluble
Esters Soluble

Density at 25°C 1,06 - 1,1 g/ml Viscosity at 25°C 200 - 800 mPa·s

This information is intended as a guideline only. For specifications please consult the Certificate of Analysis.

#### **Application and**

treat level Marke

Markets Coating industry

Machinary industry Metalworking industry Cleaning industry

Applications Coatings (upon neutralisation)

Hydraulic fluids (HFA, HFC)

Metalworking fluids (emulsions and synthetics)

Surface cleaners

Recommended dosage/usage All types of water based fluids, typical end use concentration of

0,5 - 1,5 wt. % such as:

High water based hydraulic fluids (HFA)Water glycol hydraulic fluids (HFC)

Metal working fluids (emulsions and synthetics)

Surface cleaners

· Water based emulsions (lacquers and paints)

Also suitable for mineral oil based systems, typical concentration of 0.5-1.5~wt. %

#### Key benefits

- Readily biodegradable -
- Protection of aluminium, copper and ferrous substrates.
- Excellent long-term corrosion protection in DTM formulations.
- · Prevents flash rust in alkaline systems.
- Easy to handle liquid due to the low viscosity.
- · Contains no inorganic constitutes.











### **Technical Data Sheet**

## Anticor™ C6N Corrosion Inhibitor

Article number: Verification date: Version:

A80447 18/02/2025

21

Please read Safety Data Sheet (SDS) before handling. Safety and Handling

**Product Specification** This information is available on request through our local representative.

This information is available on request through our local representative. **Packaging** 

The product should be stored at a temperature of no less than 10 °C and no more than 25 °C and away Storage

from light. For more safety details read the Safety Data Sheet (SDS)

**Quality Policy** The objective of our quality policy is the continuous fulfillment of the internal and external requirements

agreed upon with our partners with regards to everybody's performance.

The Quality System of ADDAPT® Chemicals BV is based on the principles of the NEN - EN - ISO -

Standard 9001:2015.

Liabilities All recommendations for the use of our products, whether given by us in writing, orally, or to be implied

from the results of tests carried out by us, are based on the current state of our knowledge.

Notwithstanding any such recommendations, buyer or user remains responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility thereof. Buyer has to ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with, and subject to, our general

conditions of sale and supply.

ADDAPT Chemicals BV Speltdijk 1 5704 RJ Helmond The Netherlands Tel: + 31 (0)492 597575

E-mail: info@addapt-chem.com

Home page: http://www.addapt-chem.com







